



List 53400 - PHOENIX® PMD: SA

List 78234 - PHOENIX® PMD: SS

List 52606 - PHOENIX® PMD: ASF

List 78334 - PHOENIX® PMD: SF

Side Milling & Slotting

Work Material		Tensile Strength - Hardness	Side Milling Aa: 0.393" • Ar: 0.2D		Face Milling Aa: 0.118" • Ar: 1.0D	
			Cutting Speed Vc (SFM)	Feed per Tooth fz (in/t)	Cutting Speed Vc (SFM)	Feed per Tooth fz (in/t)
P	Mild Steels, Carbon Steels (1010, 1018)	~180 HB	590 (330 - 820)	0.010 (0.008 - 0.020)	590 (330 - 820)	0.005 (0.002 - 0.008)
	Carbon Steels, Alloy Steels (1050, 4140)	~280 HB	590 (330 - 820)	0.008 (0.006 - 0.016)	590 (330 - 820)	0.004 (0.002 - 0.008)
	Die Steels (D2, H13)	~280 HB	495 (260 - 655)	0.008 (0.006 - 0.016)	495 (260 - 655)	0.004 (0.002 - 0.007)
M	Stainless Steels (Dry) (304, 420)	~250 HB	495 (260 - 655)	0.007 (0.006 - 0.016)	495 (260 - 655)	0.004 (0.002 - 0.007)
	Stainless Steels (Wet) (304, 420)	~250 HB	260 (195 - 395)	0.007 (0.006 - 0.016)	260 (195 - 395)	0.004 (0.002 - 0.007)
K	Cast Iron (FC250)	~350 N/mm ²	590 (330 - 985)	0.010 (0.006 - 0.020)	590 (330 - 985)	0.005 (0.002 - 0.008)
	Ductile Cast Iron (60-40-18)	~800 N/mm ²	590 (330 - 820)	0.006 (0.004 - 0.016)	590 (330 - 820)	0.005 (0.002 - 0.008)
N	Aluminum Alloys (6061, 7075)	~13% Si	985 (655 - 4920)	0.012 (0.008 - 0.020)	985 (655 - 4920)	0.006 (0.004 - 0.010)
S	Heat Resistant Alloys (Inconel 718)	-	115 (85 - 195)	0.006 (0.004 - 0.012)	115 (85 - 195)	0.004 (0.002 - 0.006)
	Titanium Alloy (Ti-6Al-4V)	-	130 (100 - 395)	0.007 (0.004 - 0.014)	130 (100 - 395)	0.004 (0.003 - 0.010)
H	Pre-hardened Steel (P20, Stavax)	40 - 43 HrC	330 (130 - 495)	0.007 (0.004 - 0.012)	295 (130 - 495)	0.004 (0.003 - 0.008)
	Die Cast Steels (A2, S7)	43 - 48 HrC	260 (130 - 395)	0.005 (0.003 - 0.008)	230 (130 - 395)	0.003 (0.002 - 0.006)
	Hardened Steels (D2)	50 - 55 HrC	195 (130 - 295)	0.004 (0.002 - 0.008)	165 (130 - 295)	0.002 (0.002 - 0.004)

1. Above recommended Cutting Speed is for short shank type; for long shank type, use 80% of the Cutting Speed shown in the above table.





List 53400 - PHOENIX® PMD: SA (Continued)

List 78234 - PHOENIX® PMD: SS (Continued)

List 52606 - PHOENIX® PMD: ASF (Continued)

List 78334 - PHOENIX® PMD: SF (Continued)

Counterboring & Plunging

Work Material	Tensile Strength - Hardness	Cutting Speed Vc (SFM)	Feed Rate f (in/rev)			
			Ø0.750	Ø1.000	Ø1.250	
P	Mild Steels, Carbon Steels (1010, 1018)	~180 HB	525 (330 - 655)	0.0027 (0.002 - 0.003)	0.003 (0.002 - 0.004)	0.004 (0.003 - 0.005)
	Carbon Steels, Alloy Steels (1050, 4140)	~280 HB	495 (330 - 655)	0.0027 (0.002 - 0.003)	0.003 (0.002 - 0.004)	0.004 (0.003 - 0.005)
	Die Steels (D2, H13)	~280 HB	395 (265 - 590)	0.0027 (0.002 - 0.003)	0.003 (0.002 - 0.004)	0.004 (0.003 - 0.005)
M	Stainless Steels (304, 420)	~250 HB	425 (265 - 590)	0.0027 (0.002 - 0.003)	0.003 (0.002 - 0.004)	0.004 (0.003 - 0.005)
K	Cast Iron (FC250)	~350 N/mm ²	525 (330 - 855)	0.0027 (0.002 - 0.003)	0.003 (0.002 - 0.004)	0.004 (0.003 - 0.005)
	Ductile Cast Iron (60-40-18)	~800 N/mm ²	525 (330 - 720)	0.0027 (0.002 - 0.003)	0.003 (0.002 - 0.004)	0.004 (0.003 - 0.005)
N	Aluminum Alloys (6061, 7075)	~13% Si	655 (330 - 2625)	0.0027 (0.002 - 0.003)	0.003 (0.002 - 0.004)	0.004 (0.003 - 0.005)
S	Heat Resistant Alloys (Inconel 718)	-	165 (100 - 200)	0.0027 (0.002 - 0.003)	0.003 (0.002 - 0.004)	0.004 (0.003 - 0.005)
	Titanium Alloy (Ti-6Al-4V)	-	195 (100 - 330)	0.0027 (0.002 - 0.003)	0.003 (0.002 - 0.004)	0.004 (0.003 - 0.005)
H	Pre-hardened Steel (P20, Stavax)	40 - 43 Hrc	330 (195 - 395)	0.0027 (0.002 - 0.003)	0.003 (0.002 - 0.004)	0.004 (0.003 - 0.005)
	Die Cast Steels (A2, S7)	43 - 48 Hrc	265 (130 - 330)	0.0027 (0.002 - 0.003)	0.003 (0.002 - 0.004)	0.004 (0.003 - 0.005)
	Hardened Steels (D2)	50 - 55 Hrc	195 (130 - 265)	0.0027 (0.002 - 0.003)	0.003 (0.002 - 0.004)	0.004 (0.003 - 0.005)

1. Above recommended Cutting Speed is for short shank type; for long shank type, use 80% of the Cutting Speed shown in the above table.

Maximum Processing Angle During Ramping and Helical Drilling Operations <3°

Ramping

Helical Drilling

Diameter (Inch)	Maximum Helical Milling Diameter (Inch)	Diameter (mm)	Maximum Helical Milling Diameter (mm)
Dc	D ₀ Max	Dc	D ₀ Max
0.750	1.381	20	37
1.000	1.881	25	47
1.250	2.381	32	61

