



List 5720 - A Brand ADFO: 3D


General Drilling Operations

Work Material		Carbon Steels, Mild Steels 1010, 1050, 12L14		Alloy Steels 4140, 4130		Stainless Steels 300SS, 400SS, 17-4PH		Cast Iron		Ductile Cast Iron		Aluminum Alloy 5052, 7075	
Hardness				28-35 HRC									
Drilling Speed		200-330 SFM		100-300 SFM		130-200 SFM		200-400 SFM		165-260 SFM		265-650 SFM	
Drill Dia.		Speed	Feed	Speed	Feed	Speed	Feed	Speed	Feed	Speed	Feed	Speed	Feed
mm	Inch	RPM	IPR	RPM	IPR	RPM	IPR	RPM	IPR	RPM	IPR	RPM	IPR
3	-	10,650	0.002 - 0.004	7,530	0.002 - 0.004	5,300	0.002 - 0.004	10,650	0.002 - 0.004	8,570	0.002 - 0.004	17,000	0.002 - 0.004
-	1/8	10,080	0.002 - 0.004	7,120	0.002 - 0.004	5,040	0.002 - 0.004	10,080	0.002 - 0.004	8,100	0.002 - 0.004	16,040	0.002 - 0.004
4	-	8,000	0.002 - 0.005	5,650	0.002 - 0.005	4,000	0.002 - 0.005	8,000	0.002 - 0.005	6,430	0.002 - 0.005	12,730	0.002 - 0.005
-	3/16	6,720	0.002 - 0.006	4,750	0.002 - 0.006	3,360	0.002 - 0.006	6,720	0.002 - 0.006	5,400	0.002 - 0.006	10,690	0.002 - 0.006
6	-	5,300	0.002 - 0.007	3,770	0.002 - 0.007	2,660	0.002 - 0.007	5,300	0.002 - 0.007	4,280	0.002 - 0.007	8,490	0.002 - 0.007
-	1/4	5,040	0.003 - 0.008	3,560	0.003 - 0.008	2,520	0.003 - 0.008	5,040	0.003 - 0.008	4,050	0.003 - 0.008	8,020	0.003 - 0.008
8	-	4,000	0.003 - 0.009	2,830	0.003 - 0.009	2,000	0.003 - 0.009	4,000	0.003 - 0.009	3,210	0.003 - 0.009	6,370	0.003 - 0.009
-	3/8	3,360	0.004 - 0.011	2,370	0.004 - 0.011	1,680	0.004 - 0.011	3,360	0.004 - 0.011	2,700	0.004 - 0.011	5,350	0.004 - 0.011
10	-	3,200	0.004 - 0.012	2,260	0.004 - 0.012	1,600	0.004 - 0.012	3,200	0.004 - 0.012	2,570	0.004 - 0.012	5,100	0.004 - 0.012
-	7/16	2,880	0.004 - 0.013	2,030	0.004 - 0.013	1,440	0.004 - 0.013	2,880	0.004 - 0.013	2,310	0.004 - 0.013	4,580	0.004 - 0.013
12	-	2,650	0.005 - 0.014	1,880	0.005 - 0.014	1,330	0.005 - 0.014	2,650	0.005 - 0.014	2,140	0.005 - 0.014	4,240	0.005 - 0.014
-	1/2	2,520	0.005 - 0.015	1,780	0.005 - 0.015	1,260	0.005 - 0.015	2,520	0.005 - 0.015	2,020	0.005 - 0.015	4,010	0.005 - 0.015
14	-	2,290	0.006 - 0.017	1,620	0.006 - 0.017	1,140	0.006 - 0.017	2,290	0.006 - 0.017	1,840	0.006 - 0.017	3,640	0.006 - 0.017
-	5/8	2,010	0.006 - 0.019	1,420	0.006 - 0.019	1,010	0.006 - 0.019	2,010	0.006 - 0.019	1,620	0.006 - 0.019	3,210	0.006 - 0.019
16	-	2,000	0.006 - 0.019	1,410	0.006 - 0.019	1,000	0.006 - 0.019	2,000	0.006 - 0.019	1,610	0.006 - 0.019	3,180	0.006 - 0.019
18	-	1,775	0.007 - 0.021	1,260	0.007 - 0.021	890	0.007 - 0.021	1,775	0.007 - 0.021	1,430	0.007 - 0.021	2,830	0.007 - 0.021
-	3/4	1,680	0.008 - 0.023	1,190	0.008 - 0.023	840	0.008 - 0.023	1,680	0.008 - 0.023	1,350	0.008 - 0.023	2,670	0.008 - 0.023
20	-	1,600	0.008 - 0.024	1,130	0.008 - 0.024	800	0.008 - 0.024	1,600	0.008 - 0.024	1,280	0.008 - 0.024	2,550	0.008 - 0.024

General Drilling Operations

Work Material		Cast Aluminum		Hardened Steel- Pre Hardened Steels		Plastic Mold Steels	
Hardness				Up to 50 HRC		Up to 40 HRC	
Drilling Speed		265-650 SFM		65-100 SFM		65-130 SFM	
Drill Dia.		Speed	Feed	Speed	Feed	Speed	Feed
mm	Inch	RPM	IPR	RPM	IPR	RPM	IPR
3	-	17,000	0.002 - 0.004	2,670	0.001 - 0.004	3,150	0.002 - 0.004
-	1/8	16,040	0.002 - 0.004	2,520	0.001 - 0.004	2,980	0.002 - 0.004
4	-	12,730	0.002 - 0.005	2,000	0.002 - 0.005	2,360	0.002 - 0.005
-	3/16	10,690	0.002 - 0.006	1,680	0.002 - 0.006	1,980	0.002 - 0.006
6	-	8,490	0.002 - 0.007	1,330	0.002 - 0.007	1,580	0.002 - 0.007
-	1/4	8,020	0.003 - 0.008	1,260	0.003 - 0.008	1,490	0.003 - 0.008
8	-	6,370	0.003 - 0.009	1,000	0.003 - 0.009	1,180	0.003 - 0.009
-	3/8	5,350	0.004 - 0.011	840	0.004 - 0.011	990	0.004 - 0.011
10	-	5,100	0.004 - 0.012	800	0.004 - 0.012	950	0.004 - 0.012
-	7/16	4,580	0.004 - 0.013	720	0.004 - 0.013	850	0.004 - 0.013
12	-	4,240	0.005 - 0.014	670	0.005 - 0.014	790	0.005 - 0.014
-	1/2	4,010	0.005 - 0.015	630	0.005 - 0.015	740	0.005 - 0.015
14	-	3,640	0.006 - 0.017	570	0.006 - 0.017	680	0.006 - 0.017
-	5/8	3,210	0.006 - 0.019	500	0.006 - 0.019	600	0.006 - 0.019
16	-	3,180	0.006 - 0.019	500	0.006 - 0.019	590	0.006 - 0.019
18	-	2,830	0.007 - 0.021	450	0.007 - 0.021	530	0.007 - 0.021
-	3/4	2,670	0.008 - 0.023	420	0.008 - 0.023	500	0.008 - 0.023
20	-	2,550	0.008 - 0.024	400	0.008 - 0.024	470	0.008 - 0.024

Note:



- The table above assumes a milled-flat surface and water soluble coolant.
- Use a rigid and precise machine and holder.
- Please minimize overhang length as much as possible during machining.
- Adjust the rotational speed and feed in accordance with conditions such as the machining shape, machine rigidity, or work holding.
- Please set up the drill so that the runout of the cutting edge is under 0.0008".
- Please select a cutting fluid that is most suitable for the work material with minimal smoke formation.
- In the case of dry machining, please use air blow to remove chips to prevent clogging.
 - Please do not machine stainless steel dry.
- When machining an inclined plane, adjust the rotational speed and feed in accordance with the angle of the incline (β).
 - When the machining incline angle (β) is less than 30°, please reduce the feed to 40-60%.
 - When the machining incline angle (β) is over 30°, please reduce the speed to 60-80%, the feed to 20-40%.
- Please use step drilling when drilling in pre-drilled holes to improve chip separation.
- If it is necessary to ensure the locating precision of the hole to be machined, adjust the rotational speed and feed as indicated above (in accordance with the machining precision requirement).
- Please always use the appropriate cutting fluid recommended by the cutting fluid manufacturer in the machining of magnesium alloys. Be cautious with the cutting chips as they are highly flammable and may pose a serious fire risk if not properly handled.

