



List 8630, 8730: 3xD Length of Cut

Slotting

Work Material		Aluminum Alloys, Magnesium Alloys A5052, A6061, A7075, AZ91, AZ80A		Aluminum Alloy Casting AC4C, ADC		Copper Alloy C1100	
Cutting Speed		600 ~ 1500 SFM		600 ~ 1500 SFM		300 ~ 900 SFM	
Depth of Cut		$a_a=1xD$				$a_a=0.5xD$	
Mill Dia.		Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min
Inch	mm						
-	3	25,000	70.9	25,000	70.9	19,400	55.0
1/8	-	25,000	70.9	25,000	70.9	18,300	51.9
-	4	25,000	82.7	25,000	82.7	14,500	48.0
3/16	-	24,400	92.2	24,400	92.2	12,200	46.1
-	5	23,300	96.3	23,300	96.3	11,600	48.0
-	6	19,400	96.2	19,400	96.2	9,700	48.1
1/4	-	18,300	95.1	18,300	95.1	9,200	47.8
5/16	-	14,700	97.2	14,700	97.2	7,300	48.3
-	8	14,500	95.9	14,500	95.9	7,300	48.3
3/8	-	12,200	92.2	12,200	92.2	6,100	46.1
-	10	11,600	95.9	11,600	95.9	5,800	48.0
-	12	9,700	96.2	9,700	96.2	4,800	47.6
1/2	-	9,200	95.6	9,200	95.6	4,600	47.8
5/8	-	7,300	96.6	7,300	96.6	3,700	48.9
3/4	-	6,100	98.0	6,100	98.0	3,100	49.8
1	-	4,600	91.3	4,600	91.3	2,300	45.6

1. Use a rigid and precise machine and holder.
2. The indicated speeds and feeds are for milling with water-soluble coolant.
3. Please adjust the speed and feed when the cutting depth is large or when machines with low rigidity are used.
4. Reduce speed and feed as well as depth of cut when high precision is required.
5. Please always use the appropriate cutting fluid recommended by the cutting fluid manufacturer in the machining of magnesium alloys. Be cautious with the cutting chips as they are highly flammable and may pose a serious fire risk if not properly handled.

Side Milling

Work Material		Aluminum Alloys, Magnesium Alloys A5052, A6061, A7075, AZ91, AZ80A		Aluminum Alloy Casting AC4C, ADC		Copper Alloy C1100	
Cutting Speed		800 ~ 2200 SFM		800 ~ 2200 SFM		600 ~ 1200 SFM	
Depth of Cut		$a_a=3xD \cdot a_r=0.1xD$					
Mill Dia.		Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min
Inch	mm						
-	3	25,000	79.7	25,000	79.7	25,000	79.7
1/8	-	25,000	88.6	25,000	88.6	25,000	88.6
-	4	25,000	102.8	25,000	102.8	21,800	89.6
3/16	-	25,000	118.1	25,000	118.1	18,300	86.5
-	5	25,000	128.4	25,000	128.4	17,500	89.9
-	6	25,000	154.1	25,000	154.1	14,500	89.4
1/4	-	25,000	162.4	25,000	162.4	13,700	89.0
5/16	-	20,800	172.0	20,800	172.0	11,000	90.9
-	8	20,600	169.3	20,600	169.3	10,900	89.6
3/8	-	17,300	163.5	17,300	163.5	9,200	86.9
-	10	16,500	169.5	16,500	169.5	8,700	89.4
-	12	13,700	168.9	13,700	168.9	7,300	90.0
1/2	-	13,000	168.9	13,000	168.9	6,900	89.7
5/8	-	10,400	172.0	10,400	172.0	5,500	90.9
3/4	-	8,700	174.7	8,700	174.7	4,600	92.4
1	-	6,500	161.2	6,500	161.2	3,400	84.3

1. Use a rigid and precise machine and holder.
2. The indicated speeds and feeds are for milling with water-soluble coolant.
3. Please adjust the speed and feed when the cutting depth is large or when machines with low rigidity are used.
4. Reduce speed and feed as well as depth of cut when high precision is required.
5. Please always use the appropriate cutting fluid recommended by the cutting fluid manufacturer in the machining of magnesium alloys. Be cautious with the cutting chips as they are highly flammable and may pose a serious fire risk if not properly handled.

