



## List VG441BN: 4 Flute - Ball Nose

### Side Milling

Hardness	<25 HRC		25-30 HRC		30-35 HRC		35-45 HRC		45-50 HRC		<40 HRC		<45 HRC	
Work Material	Mild Steels Carbon Steels Cast Iron		400 Stainless Steels Alloy Steels Tool Steels		300 Stainless Steels Hardened Steels Pre-hardened Steels		PH Stainless Steels Hardened Steels		Hardened Steels		Titanium Alloys		High Temp. Alloys Inconel Hastelloy	
Cutting Speed	400-500 SFM		300-400 SFM		200-350 SFM		200-250 SFM		175-225 SFM		150-250 SFM		100-135 SFM	
Depth of Cut	Aa=1.5D Ar=0.5D						Aa=1.25D Ar=0.4D		Aa=1.25D Ar=0.2D		Aa=1.25D Ar=0.4D		Aa=1D Ar=0.2D	
Mill Dia.	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min
1/8	13,750	44.0	10,695	25.7	8,400	18.6	6,875	15.2	6,110	14.5	6,110	12.9	3,665	9.5
3/16	9,170	46.8	7,130	28.8	5,600	20.6	4,585	16.9	4,075	16.3	4,075	13.7	2,445	10.9
1/4	6,875	46.8	5,350	31.1	4,200	20.3	3,440	16.7	3,050	16.8	3,050	13.9	1,835	11.2
5/16	5,500	48.1	4,210	31.8	3,350	21.4	2,750	17.6	2,450	17.8	2,450	15.1	1,465	11.7
3/8	4,585	47.1	3,565	30.5	2,800	20.6	2,290	16.9	2,040	16.3	2,040	14.6	1,220	11.1
7/16	3,930	45.4	3,055	30.2	2,400	20.1	1,965	16.5	1,750	16.3	1,750	14.0	1,050	11.1
1/2	3,440	45.4	2,675	29.2	2,100	19.5	1,720	15.9	1,525	15.7	1,525	13.9	915	10.8
5/8	2,750	40.6	2,140	27.7	1,700	19.0	1,375	15.4	1,225	14.7	1,225	12.5	730	9.9
3/4	2,290	37.3	1,785	25.3	1,400	16.8	1,150	13.8	1,025	13.5	1,025	11.8	610	9.3
1	1,720	33.0	1,340	22.8	1,050	14.9	860	12.2	765	12.2	765	10.6	460	8.4
1 1/4	1,375	26.4	1,070	18.2	850	12.1	690	9.8	610	9.7	610	8.3	365	6.7

### Slotting

Hardness	<25 HRC		25-30 HRC		30-35 HRC		35-45 HRC		45-50 HRC		<40 HRC		<45 HRC	
Work Material	Mild Steels Carbon Steels Cast Iron		400 Stainless Steels Alloy Steels Tool Steels		300 Stainless Steels Hardened Steels Pre-hardened Steels		PH Stainless Steels Hardened Steels		Hardened Steels		Titanium Alloys		High Temp. Alloys Alloys Inconel Hastelloy	
Cutting Speed	325-400 SFM		250-325 SFM		175-275 SFM		160-200 SFM		140-180 SFM		125-200 SFM		75-100 SFM	
Depth of Cut	Aa=1D						Aa=0.75D		Aa=0.5D		Aa=0.5D		Aa=0.2D	
Mill Dia.	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min	Speed RPM	Feed in/min
1/8	11,240	35.8	8,860	21.3	6,900	15.4	5,500	10.7	4,890	11.6	5,050	10.6	2,750	7.3
3/16	7,495	38.5	5,910	23.9	4,600	17.5	3,670	11.5	3,260	12.8	3,350	11.5	1,835	8.1
1/4	5,620	37.9	4,430	25.5	3,450	17.2	2,750	12.2	2,445	14.0	2,550	11.8	1,375	8.1
5/16	4,500	39.4	3,545	26.8	2,750	18.3	2,200	12.9	1,955	14.2	2,000	11.8	1,100	9.0
3/8	3,750	38.2	2,955	25.5	2,300	17.5	1,835	12.2	1,630	12.8	1,700	11.6	915	8.3
7/16	3,210	37.1	2,530	24.7	1,950	16.7	1,575	11.8	1,395	12.8	1,450	11.8	785	8.3
1/2	2,810	37.2	2,215	24.2	1,700	16.1	1,375	11.5	1,225	12.8	1,300	12.1	690	8.1
5/8	2,250	33.1	1,775	22.5	1,400	15.9	1,100	11.0	975	11.6	1,000	10.0	550	7.6
3/4	1,875	31.1	1,480	20.9	1,150	14.4	920	10.0	815	10.5	850	9.4	460	6.9
1	1,405	26.7	1,110	18.7	875	12.6	685	8.6	610	9.8	650	9.0	345	6.5
1 1/4	1,115	21.2	885	14.9	700	10.1	550	6.9	490	7.8	500	6.9	275	5.1

ABOUT OSG

DRILLING

THREADING

MILLING

HOLDERS

INDEX

